

Technical Information

RC 60

F Class, Red Insulating Varnish, Air Drying

Product Description

ASV®RC 60 red insulating varnish is a coating with exceptional insulating properties for electrical and electronic equipment to provide surface protection against oils, water, moisture, acids, alkalis and varying temperatures. Dry to touch in 10 minutes after application, and tack free within 45 minutes, this fast air drying, flexible coating has excellent adhesion to metal windings and coils with a temperature Class F (155°C) rating and high dielectric strength.

ASV®RC 60 offers complete surface protection by sealing out water and moisture while possessing excellent penetrating and adhesive properties along with resistance to oils.

Applications

- Use ASV®RC 60 protective coating to insulate and seal:
- Motor Windings
- Terminals
- Bus Bars
- Commutator Ends
- Stator Coils
- End Turns on Electrical Windings
- Printed Circuit Boards
- Rewound Motors
- Generators
- Transformers
- Phenolic / Porcelain Molded Parts
- Magnets
- Improving Megaohm and dielectric values of new as well as rebuilt motors
- Highly suitable for insulating electrical windings that are exposed to extreme moisture and corrosive conditions as well as temperature and voltage fluctuations

Benefits

- Possesses high dielectric strength, surface and volume resistivity to provide effective insulation of electrical equipment
- Hard, durable & flexible protective film does not peel, crack or age and offers protective resistance to shocks, abrasion as well as aggressive chemical environments
- Fast air-drying, stable, single component coating with excellent resistance against oils, chemicals, ageing, moisture condensation, weathering effects
- Seals out moisture with a visible, highly glossy, smooth abrasion resistant protective coating
- Highly heat resistant coating suitable for Class F insulation with greater allowance for thermal expansion and contraction
- Improves Megaohm and dielectric values
- Very good adhesion on a variety of substrates
- Oil resistant to ASTM D 115

Directions for Use

Shake can well before use. Clean thoroughly and dry the surface to be coated before application of this coating. Mask area not to be sprayed. Spray from 12-15 inches away in light, even coats with a sweeping action of the hand. Allow solvents to evaporate completely before re-application. Additional coats for heavy film can be applied when first coat is dry. Coating becomes dry to touch in about 20-30 minutes. Clean the valve by inverting the can and spraying a few short bursts till only the clear propellant comes out. Clean the actuator button orifice by means of a thin, fine wire.

Caution: Contains flammable solvents and propellant. Do not spray near naked flame, hot surfaces or energized equipment. Use with adequate ventilation.

Technical Information

RC 60

F Class, Red Insulating Varnish, Air Drying

Technical Properties

Description Appearance Glossy finish Class F Type Fast air drying coating Adhesion Excellent Color Red Color Fastness Excellent Percent Solids (By Weight) Odor Specific Gravity @ 20°C Flash Point Drying Time Schedule @ 25°C -To Touch -To Handle -Full Cure Insulating varnish Insulating varnish After drying varnish After drying table 19 Fast air drying coating Excellent Days desire to least the seal to	
Class F Type Fast air drying coating Adhesion Excellent Color Red Color Fastness Excellent Percent Solids (By Weight) 19 minimum Odor Solvent Specific Gravity @ 20°C Flash Point Drying Time Schedule @ 25°C -To Touch 10-20 minutes -Full Cure Fast air drying coating Excellent - Red - Color Fastness - Fast air drying coating - To Handle - Solvent - 19 minimum - 10 - 20 minutes - Full Cure - 24 hours (for optimum results)	
Type Fast air drying coating Adhesion Excellent Color Red Color Fastness Excellent Percent Solids (By Weight) 19 minimum Odor Solvent Specific Gravity @ 20°C 0.90 - 1.05 gm/cc Flash Point -18°C (aerosol) Drying Time Schedule @ 25°C -To Touch 10-20 minutes -To Handle 50-60 minutes -Full Cure 24 hours (for optimum results)	
Adhesion Excellent Color Red Color Fastness Excellent Percent Solids (By Weight) 19 minimum Odor Solvent Specific Gravity @ 20°C 0.90 - 1.05 gm/cc Flash Point -18°C (aerosol) Drying Time Schedule @ 25°C -To Touch 10-20 minutes -To Handle 50-60 minutes -Full Cure 24 hours (for optimum results)	
Color Fastness Excellent Percent Solids (By Weight) 19 minimum Odor Solvent Specific Gravity @ 20°C 0.90 - 1.05 gm/cc Flash Point -18°C (aerosol) Drying Time Schedule @ 25°C -To Touch 10-20 minutes -To Handle 50-60 minutes -Full Cure 24 hours (for optimum results)	
Color Fastness Excellent Percent Solids (By Weight) 19 minimum Odor Solvent Specific Gravity @ 20°C 0.90 - 1.05 gm/cc Flash Point -18°C (aerosol) Drying Time Schedule @ 25°C -To Touch 10-20 minutes -To Handle 50-60 minutes -Full Cure 24 hours (for optimum results)	
Percent Solids (By Weight) Odor Solvent Specific Gravity @ 20°C Flash Point Drying Time Schedule @ 25°C -To Touch To Handle -Full Cure 19 minimum 19 minimum 10-80 gm/cc -18°C (aerosol) 10-20 minutes 24 hours (for optimum results)	
Odor Solvent Specific Gravity @ 20°C 0.90 - 1.05 gm/cc Flash Point -18°C (aerosol) Drying Time Schedule @ 25°C -To Touch 10-20 minutes -To Handle 50-60 minutes -Full Cure 24 hours (for optimum results)	
Specific Gravity @ 20°C 0.90 - 1.05 gm/cc Flash Point -18°C (aerosol) Drying Time Schedule @ 25°C -To Touch 10-20 minutes -To Handle 50-60 minutes -Full Cure 24 hours (for optimum results)	
Flash Point -18°C (aerosol) Drying Time Schedule @ 25°C -To Touch 10-20 minutes -To Handle 50-60 minutes -Full Cure 24 hours (for optimum results)	
Drying Time Schedule @ 25°C -To Touch 10-20 minutes -To Handle 50-60 minutes -Full Cure 24 hours (for optimum results)	
-To Touch 10-20 minutes -To Handle 50-60 minutes -Full Cure 24 hours (for optimum results)	
-To Handle 50-60 minutes -Full Cure 24 hours (for optimum results)	
-Full Cure 24 hours (for optimum results)	
Describer Davied After device to bondle	
-Recoating Period After drying to handle	
Resistant to Mineral oils, mineral spirits, humidity	
Temperature Range -40°C to +155°C	
Evaporation Rate > n,butyl acetate	
Vapor Pressure (air=1) >air	
Dielectric Strength 2100 volts/mil	
Dry Film Thickness (DFT) 25-30 microns per coat	
Coverage(aerosol) 2-3 m²/can	
Propellant Hydrocarbon	
Shelf Life 1 year	

^{*} of active ingredients

ASV MULTICHEMIE PRIVATE LIMITED

Distributed by:

Registered Office: 327, Arun Chambers, Tardeo Road, Tardeo, Mumbai-400 034, INDIA
Tel: +91 (022) 2764 2514 | Fax: +91 (022) 2352 6318 | E-mail: info@asymultichemie.com
MOLYSULF®& ASV® Specialty Lubricants & MRO Technical Chemicals.
® Registered trademark of ASV Multichemie Private Limited, INDIA.
THIS PRODUCT IS DEVELOPED AND MANUFACTURED BY US FOR INDUSTRIAL USE ONLY.



Technical Information

RC 60

F Class, Red Insulating Varnish, Air Drying

Available Packaging

- 4 liter container
- 500 ml aerosol spray

General

Use in well ventilated areas. Avoid continuous breathing of vapor and spray mist. In closed areas or areas with poor ventilation, use respiratory protection. For complete details on safety, short and long term exposure, refer to this product's safety data sheet (SDS).

Disposal

All used and unused product should be disposed of in accordance with state regulations.

Shelf Life

Bulk - 12 months from date of manufacture in sealed condition Aerosol - 24 months from date of manufacture

Handling

Read instructions on the container label of the product before use. The product safety data sheet (SDS) contains the relevant information regarding personal protective equipment, safe use, physical and health hazards. Safety data sheet is available from ASV or your local ASV distributor.

Limited Warranty

The information and data contained in this sheet is accurate to the best of our knowledge or is obtained from sources, tests or experiences believed by us to be reliable and accurate. User is responsible for determining whether recommended ASV® product is fit for a particular purpose. All products should be tested for suitability on a particular application prior to actual use. We make no representations of any kind. Data offered without warranty.