# WEICONLOCK® AN 305-74 Flange Sealing



# high viscosity high strength hard to disassemble

Gasketing of flanges, gearboxes and other motor housings

# **Technical Data**

Colour	orange
Viscosity at 25°C (+77°F) according to Brookfield	30.000 - 100.000 ht mPa·s
Max. Gap Bridging	0,5 mm
Breakaway strength (Thread)	16 - 24 Nm
Prevailing stregth	5 - 10 Nm
Shear strength Nmm <sup>2</sup> (DIN 54452)	5 - 10 N/mm²
Handling strength at room temperature	15 - 30 min.
Final strength (100%) after	12 h
Temperature resistance	-60 to +180 °C
ISSA-Code	75.628.24/25
IMPA-Code	815212/13

\*Strength values based on M 10 screws, 8.8 grade, thickness of nut 0,8.d Static shear strength based on cylindrical parts of abt. Ø 13 mm, tolerance (D-d) = 0,05 mm, I/d = 0,88

# Surface pre-treatment

In general, WEICONLOCK does not require special pre-treatment as slightly oily surfaces (e.g. on as received parts) will be tolerated. However, best results will be achieved on cleaned, degreased parts (use WEICON Surface Cleaner). If required, the parts should be slightly roughened.

## Processing

WEICONLOCK is ready for use and should be applied evenly direct from the bottle/tube with the dispensing tip (avoid direct contact of dispensing tip with metal). Apply continuous bead on one side

### Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON GmbH & Co. KG WEICON Middle East L.L.C. (Headquarters) Germany phone +49 (0) 251 9322 0 info@weicon.de

WEICON SA (Pty) Ltd South Africa phone +27 (0) 21 709 0088 info@weicon.co.za www.weicon.co.za

www.weicon.de

United Arab Emirates phone +971 4 880 25 05 info@weicon.ae www.weicon.ae

WEICON South East Asia Pte Ltd Singapore phone (+65) 6710 7671 info@weicon.com.sg www.weicon.com.sg

WEICON Inc. Canada phone +1 877 620 8889 nfo@weicon www.weicon.ca

WEICON Czech Republic s.r.o. Czech Republic phone +42 (0) 417 533 013 info@weicon.cz www.weicon.cz

WEICON Kimya Sanayi Tic. Ltd. Şti. Turkey phone +90 (0) 212 465 33 65 info@w www.weicon.com.tr

WEICON Ibérica S.L. Spain phone +34 (0) 914 7997 34 info@weicon.e www.weicon.es

WEICON Romania SRL Romania phone +40 (0) 3 65 730 763 office@wei www.weicon.com.ro

WEICON Italia S.r.I. Italy phone (+39) 0102924871 info@weicon www.weicon.it

of flange, join and tighten parts quickly. For sealing applications (pipe fitting) apply WEICONLOCK in circular motions on the thread. Screw pipe threads together and tighten until desired orientation. Do not pour back into the bottle any WEICONLOCK fluid which had contact with metal; even smallest metal particles will cause the content of the bottle to cure. In series construction, the use of manual or automatic applicators is recommended.

# Storage

WEICONLOCK can be stored in the unopened original container for at least 24 months at room temperature. Keep away from heat sources and direct sunlight. The air in the bottle/tube keeps WEICONLOCK liquid.

# Safety and health

When using WEICON products, the physical, safety technical, toxicological and ecological data and regulations in our EC safety data sheets (www.weicon.com) must be observed.

# Available sizes

30574150	WEICONLOCK® AN 305-74 Flange Sealing 50 ml
30574200	WEICONLOCK® AN 305-74 Flange Sealing 200 ml
30574300	WEICONLOCK® AN 305-74 Flange Sealing 300 ml
A	

# Accessories:

30700200 30955172

Activator F, 200 ml Dosing Tips, Size 1